

### Characteristics

- High flow
- High impact
- Powder

Property	Value	Unit	Method
Melt Index, MI <sub>2</sub>	5	g/10min	D 1238
Specific Gravity	1.04		D 792
Tensile Strength	400	kg/cm <sup>2</sup>	D 638
Flexural Strength	680	kg/cm <sup>2</sup>	D 790
Flexural Modulus	22000	kg/cm <sup>2</sup>	D 790
Rockwell Hardness	R-101		D 785
Izod Impact Strength	30	kg-cm/cm	D 256
Vicat Softening Point	99	°C	D 1525
Heat Deflection Temperature	84	°C	D 648

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

**GLOBAL PLASTICS LP**

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

[www.globalplastics.net](http://www.globalplastics.net)