

Blending

Applications

- Adhesives
- Sealants
- Wax blends
- Industrial sealants

Characteristics

- Excellent compatibility with hydrocarbons
- Excellent compatibility with most waxes
- Excellent compatibility with natural tackifiers
- Designed for making hot melt adhesives

| Property | Value | Unit | Method |
|-----------------------------|-------|-------------------|--------|
| Melt Index, MI ₂ | 100 | g/10min | D 1238 |
| Density | 0.946 | g/cm ³ | D 1505 |
| Vinyl Acetate Content | 28 | % | |
| Tensile Strength at Break | 6300 | psi | D 638 |
| Elongation at Break | 640 | % | D 638 |
| 1% Secant Modulus | 1900 | psi | D 790 |
| Durometer Hardness, Shore A | 72 | | D 2240 |
| Durometer Hardness, Shore D | 16 | | D 2240 |

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net