

### Blending

#### Applications

- Adhesives
- Sealants
- Wax blends
- Industrial sealants

#### Characteristics

- Excellent compatibility with hydrocarbons
- Excellent compatibility with most waxes
- Excellent compatibility with natural tackifiers
- Designed for making hot melt adhesives

Property	Value	Unit	Method
Melt Index, $MI_2$	400	g/10min	D 1238
Density	0.941	g/cm <sup>3</sup>	D 1505
Vinyl Acetate Content	28	%	
Tensile Strength at Break	200	psi	D 638
Elongation at Break	500	%	D 638
1% Secant Modulus	1900	psi	D 790
Durometer Hardness, Shore A	60		D 2240

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

**GLOBAL PLASTICS LP**

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

[www.globalplastics.net](http://www.globalplastics.net)