

Injection Molding

Applications

- Cosmetic packaging
- Personal care packaging
- Container closures
- Furniture and furniture trim
- Food packaging
- Toys and sporting goods

Characteristics

- Easy processability on automatic molding equipment
- Excellent gloss
- Excellent clarity
- Warpage resistance

Property	Value	Unit	Method
Melt Index, MI_2	20	gm/10min	D 1238
Density	0.920	g/cm ³	D 4883
Tensile Strength at Break	1200	psi	D 638
Elongation at Break	90	%	D 638
Flexural Modulus	33000	psi	D 638

FDA Status: This resin complies with FDA regulation 21 CFR 177.1520 (c) 3.1a, and may be used as articles or components of articles intended for packaging or holding food, except during cooking.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net