

### Compounding and Color Concentrates

LLDPE 20924 G is a granular form resin designed for compounding and color concentrates.

Property	Value	Unit	Method
Melt Index, (condition 190°C/2.16 kg)	20	gm/10min	D 1238
Density	0.924	g/cm <sup>3</sup>	D 1505
Brittleness Temperature	<-75	°C	D 746
1% Secant Modulus	315	MPa	D 638
Tensile Strength @ Yield	2100	psi	D 638
Tensile Strength @ Break	1100	psi	D 638
Tensile Elongation @ Break	60	%	D 638
Hardness, Shore D	55		D 2240
ESCR (100% Igepal) F <sub>50</sub>	24	Hrs	D 1693A

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

**GLOBAL PLASTICS LP**

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

[www.globalplastics.net](http://www.globalplastics.net)