

FDA Status: 21 CFT 177.1500

Property	Value	Unit	Method
Melt Index, MI ₂	6	g/10min	D 1238
Density	1.14	g/cm ³	D 792
Tensile Strength	66	Mpa	D 638
Elongation	260	%	D 638
Flexural Modulus	1560	Mpa	D 790
Izod Impact Strength, Notched	65	J/m	D 256
Molding Shrinkage, Normal	0.8	%	D 955
Molding Shrinkage, Parallel	0.8	%	D 955
Hardness, Shore D	75		D 2240
Melting Point	220	°C	

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility. User must make their own decisions regarding its suitability for their equipment and final products.

GLOBAL PLASTICS LP

21 Downing Street Front 1 New York, NY 10014

(Domestic) 1-800 417-4605

(International) +1-646-790-7200

www.globalplastics.net